



2K AUTO PRIMER

Material Safety Data Sheet

A two pack high quality primer formulated for use automotive refinish and industry.

Research and Development Department
Master Paint Industries (Pvt.) Ltd.
Phone : 0 4 2 – 111 – 333 – 465,
E-Mail : info@masterpaints.com



PRODUCT INFORMATION

Description: A two pack high quality primer formulated for use automotive refinish and industry.

TECHNICAL INFORMATION:

Colour	Assorted
Finish	Matt to Silk
Generic Type	Polyurethane
Vol Solid	38 %
Mixing Ratio	3: 1
Spreading Rate	12.7 m ² / L. @100 µm dft.
Drying Time	½ hr. at 30 °C.
Recoating Time	4 - 6 hrs.
Pot Life	4 hrs.
Thinner / cleaner	P.U thinner
Weight / Litre	1.30 kg of mix.
Flash Point	27 °C, 85.5 °F
Further coat	Coat on coat
Packing size	3.64 litrs kit.

APPLICATION DETAIL :

Mix individual components to uniform consistency, then combine in recommended ratio. Thin as required for spray or by rag application with recommended thinner. Do not thin separately packed components. Use of thinner other than that specified or recommended may adversely affect the product performance. Mix only that quantity which is supposed to be consumed within the pot life of paint.

TYPICAL SURFACES :

Prepared and primed surfaces. Ensure surface is dry and clean from contaminants.

SAFETY AND ENVIRONMENTAL NOTES:

Ensure proper ventilation during application and drying of paint. Avoid inhalation of paint mist and vapours and skin contact. Spillage of paint on skin should immediately be removed with suitable cleanser soap and water. Eyes should be well flushed with water and immediate medical attention should be sought.

